

Reply to Comment on "Microscopic theory of network glasses"

In the preceding Comment[1], Micoulaut and Boolchand (MB) compare our predictions[2] on glass transitions in network systems for the ratios of the transition temperatures T_A/T_G and T_K/T_G with experimental data for $\text{Ge}_x\text{Se}_{1-x}$. T_A is the temperature at which "landscape dominated" activated dynamics begins and T_K is the ideal glass temperature where an entropy crisis occurs. T_G is the temperature where the kinetic glass transition occurs in the laboratory. MB claim significant differences between experiment and theory are seen and claim the lack of agreement is due to the failure of our theory to include "local structures, structural self-organization, and non-central forces".

The T_K/T_G is ratio shown in Fig. 1 of [1] and obtained from Angell's group[3]. Examination of Fig. 1 in fact shows remarkable agreement between experiment and theory. Not only is the decrease in T_K/T_G with n_b (the average number of bonds/atom) reproduced by the theory but the difference between experiment and theory is at most 10%. In light of the admitted simplifications in the theory (as discussed below), the comparison lends strong support to the theory. Our theory did not predict the detailed dynamics beyond the degree of bonding where rubber behavior ensues but this "overconstrained" behavior is precisely what Angell claims to begin for $n_b > 2.4$ in the $\text{Ge}_x\text{Se}_{1-x}$ system and is claimed to be the origin of the minimum discussed by MB. Quantitatively, our n_b rigidity limit is $n_b = 2.9$.

On the other hand, the comparison of T_A/T_G ratios made by MB is misleading because the T_A defined by them is not the T_A defined in the random first order transition theory of glasses. MB define T_A as the temperature at which non-ergodic behavior in $\dot{H}$ is not apparent. Their lack of non-ergodicity is equated to a lack of activated behavior. Yet whether non-ergodicity is seen depends on the time scale of scanning in the experiment

and is thus not a landscape parameter like T_A which does not depend on the measurement time scale but rather signals the origin of activated behavior with rate slower than local vibrations. The temperature at which the viscosity of $\text{Ge}_x\text{Se}_{1-x}$ begins to show activated behavior must be considerably greater than 10% higher than T_G , as would be suggested by the plots in the preceding Comment. Lubchenko and Wolynes[4] show that T_A occurs for most substances at a temperature higher than that at which the viscosity is 100 poise. Extrapolating the Angell viscosity data[3] of either the ternary mixture GeAsSe or GeSe (inset b of Fig 2 in Ref.[3]) to 100 poise, gives a T_A at least 1.7 times T_G . Nevertheless we agree and pointed out in our Letter that the predicted T_A/T_G for soft repulsive spheres with fixed harmonic connections is too large for real molecular systems. Density fluctuations, the breakdown of fixed bonding relations as the boiling point is approached, and attractive forces will clearly affect the predictions of our theory (which included only a soft repulsion), as discussed in our Letter. Our prediction is thus merely saying the entire liquid regime encompasses activated behavior for substances with sufficient bonding. We point out that Angell suggests that liquids become "stronger" as n_b is increased, again just as our theory predicts.

MB suggest several features that are lacking from our theory. Two of these, local structure (by which we assume MB mean lack of complete chemical mixing) and non-central forces (bond-bending), were explicitly mentioned by us, but not included in the calculations so as to highlight the basic physics. These can be easily included. "Structural self-organization" by which MB apparently mean large scale structure formation in the network was not discussed in our Letter. Phenomena of this type ("polyamorphism") seem to occur in several glassy fluids. They may be essential to the glass transition. On the other hand, in our view, it is likely that these are consequences of the low configurational entropy density near T_G which

allows weak forces to cause large scale ordering. There is no reason to believe the glass transition is the only transition possible in a fluid phase and we do not mean to imply that it is.

In summary, the T_K/T_G comparison made by MB provides strong evidence for the validity of the random first order transition theory of network liquids, while the T_A/T_G comparison is based on the misidentification of T_A with a nonequilibrium scan time scale dependent quantity and is not valid. Estimating T_A/T_G from viscosity data provides evidence that the trends of how T_A/T_G varies with bonding are indeed reproduced by our theory but quantitative improvements are needed. Extensions of the theory to include the effects of attractive forces, bond-bending and complex local structure formation are not hard to develop.

R.W. Hall¹ and P.G. Wolynes²

¹ Department of Chemistry, Louisiana State University, Baton Rouge, Louisiana 70803-1804

² Department of Chemistry and Biochemistry, University of California, San Diego, La Jolla, California 92093-0332

PACS numbers: 61.43.Fs, 64.70.Pf, 65.60.+a

-
- [1] M. Micoulaut and P. Boolchand, Phys. Rev. Lett. **to appear** (2003).
 - [2] R. Hall and P. Wolynes, Phys. Rev. Lett. **90**, 085505 (2003).
 - [3] M. Tatsumisago, B. Halfpap, J. Green, S. Lindsay, and C. Angell, Phys. Rev. Lett. **64**, 1549 (1990).
 - [4] V. Lubchenko and P. Wolynes, Cond. Mat. 0307089, J. Chem. Phys., in press (2003).